


ANGLE PROFILES RANGE

GENERAL DESCRIPTION



High quality cold formed profiles, made of certified galvanized steel sheet.

SCOPE OF APPLICATION


- Perimeter profile in simple structure gypsum board continuous ceilings.
- Perimeter profile in double structure gypsum board suspended continuous ceilings.
- Perimeter profile in gypsum board lining systems.
- L25/25 P: Perforated angle for corner reinforcement.

BENEFITS


- Return lips to avoid cuts and accidents during assembly.
- Quality certified steel sheet rolled by the leading European steel company.

PRODUCT RANGE



CR2
L30/25



L24/24
L30/30
L35/30 R
L34/34



L25/25 P



PROFILE	THK (mm)	DIMENSIONS		Units/pallet	CE	NF	AENOR
		a	b				
CR2	0.55	34	23	200	●	●	●
L30/25	0.55	30	25	432	●	●	
L24/24	0.55	24	24	432	●		●
L30/30	0.55	30	30	600	●	●	●
L35/30 R	0.55	35.5	30.5	390	●	●	●
L34/34	0.55	34	34	432	●	●	●
L25/25 P	0.55	25	25	100			

Standard lenght: 3,000 mm.

Other gauges and lenghts on demand.

ANGLE PROFILES RANGE

TECHNICAL FEATURES

- Steel grade DX51 D (according to EN 10346 standard).
- Galvanisation type Z140 (140 g/m²).
- Galvanisation type Z275 (275 g/m²) or Aluzinc type AZ100 (100 g/m²) for profiles with NF certification.

FIRE REACTION AND ACOUSTICS

- Fire reaction: Euroclass A1 (non combustible).
- Acoustic and fire reaction of Kingspan systems have been accredited by laboratory testing.

STORAGE CONDITIONS

- Store on flat and sheltered surfaces.
- Do not expose to rain or direct sunlight.

MANUFACTURING STANDARDS

- All products have the CE marking according to EN 14195:2005.

Additionally, some of the products have the following voluntary certifications (see table):

- AENOR N mark according to instruction RP 35.12.
- NF mark by CSTB according to instruction NF411.



Download the latest version by scanning the QR code or by clicking [here](#)

Teczone Española S.A.U. reserves the right to modify the contents of this document without any prior warning. Every effort has been made to ensure that the content of this publication is accurate, but Teczone Española S.A.U. and its affiliated companies are not responsible for errors or information that may be misleading. Suggestions regarding the final use or application of the products or work methods are merely informative and Teczone Española S.A.U. and its affiliates do not accept any responsibility in this regard.